




LAMINATION

EI-375



Tolerance : ± 0.08mm

(All dimensions in mm)

PROPERTIES OF SQUARE STACK

MAGNETIC DESIGN FORMULAR

$$B_{max} = 407 \times 10^3 / K_1 N \text{ (Gauss per Volt at 60Hz)}$$

(N= Number of turns)

$$H_o = (0.168 \times 10^{-3}) N \text{ Oersted per milliampere}$$

of direct current in winding

$$L = (0.155 \times 10^{-8}) K_1 N^2 \mu \text{ ac Henries}$$

MAGNETIC PATH DIMENSION

$$l = 7.44 \text{ cm}$$

$$A = 0.922 \text{ cm}^2$$

K₁ (STACKING FACTOR)

Thickness (mm)	Butt Jointed	Interleaved one per layer
0.1	0.90	0.80
0.2	0.90	0.85
0.35	0.95	0.90

MATERIAL GRADE	THICKNESS(mm)	WEIGHT AND NUMBERS	
		g/pcs	pcs/kg
PC (Ni80%Mo5%)	0.195t	0.1256	7,959
	0.345t	0.2223	4,498
PB (Ni45~48%)	0.195t	0.1185	8,437
	0.345t	0.2097	4,769